


## MICROCUT®

For sophisticated processing in microerosion

- The high-tensile steel core of microcut® reliably sustains high wire pre-loads, even with the smallest diameters
- Functional layer composition for finest machining with absolute reproducibility

### Technical data

Core	Copper-cladded steel
Coating	CuZn50, outer layer Ag
Tensile strength	2.000 MPa / 290,000PSI
Elongation	1%
Color	Gold



### Delivery program

Diameter [mm]	0,02-0,10	0,05-0,10	0,07	0,08	0,09	0,10
BK100: 5.000 m	●					
BK100: 10.000 m		●				
bedra4: 20.000 m			●	●	●	●
bedra4: 30.000 m			●	●	●	●